

M1.02.0 Special Borrow.

Special Borrow shall consist of one of the following:

a) A native in-situ soil that is classified under AASHTO M 145 as A-3, or that portion of A-1 and A-2 with less than 12% passing the 75 µm sieve as determined by AASHTO T 11 and T 27. Maximum size of stone for testing purposes shall be 75 millimeters (nominal). For Muck Backfill only, 15% or less passing the 75 µm sieve will be allowable.

b) A crushed rock, either obtained from ledge excavation on the project or other approved sources, that meets the following requirements:

Percent of wear, L.A. Abrasion Test	50% Maximum
Plasticity Index	6% Maximum

Gradation Requirements

Sieve Designation	Percent Passing
150 mm	100
50 mm	90 - 100
4.75 mm	20 - 65
75 µm	0 - 12

c) The use of Processed Glass Aggregate (PGA) meeting the requirements of M2.01.08 may be blended with either special borrow material outlined above. An addition rate of 10% by mass in areas where the borrow will not be exposed will be allowed, providing the physical characteristics are maintained. The PGA will be blended so as to produce a homogeneous borrow material.